



ABS-X

ABS-X is our take on a next-generation ABS filament. By applying our zero-warp technology to the filament we have created a filament with far less cracking, proven near perfect interlayers, reliable bed adhesion (glass, tape & other adhesives) while improving the mechanical properties making ABS-X extra strong. These properties make ABS-X the ultimate ABS replacement that prints strong and beautiful parts on any FDM 3D printer without the common headaches associated with regular ABS like warping & horrible bed adhesion. ABS-X is the perfect material for strong objects that require a high impact tolerance.

Material features:

- Zero warp technology
- Excellent interlayer adhesion
- Reliable bed adhesion (Glass, tape & other adhesives)
- Enhanced mechanical properties over regular ABS
- Great strength & aesthetics

Colours:

ABS-X is available from stock in 12 colours. Other colours on request.



Packaging:

ABS-X is available in 750g, 1kg and 2,3kg

Filament specs.

Size	Ø tolerance	Roundness
1,75mm	± 0,05mm	≥ 95%
2,85mm	± 0,10mm	≥ 95%

Material properties

Description	Testmethod	Typical value
Specific gravity	ISO 1183	1,1 g/cc
MFI 260°C/5 kg	ISO 1133	41 g/10 min
Tensile strength at yield	ISO 527	40 MPa
Tensile strength at break	ISO 527	25,5 MPa
Elongation strain at break	ISO 527	10%
Elongation strain at yield	ISO 527	2,9%
Tensile (E) modulus	ISO 527	1980 MPa
Impact strength - Charpy method 23°C (notched)	ISO 179 1eA	58 kJ/m ²
Printing temp.	Internal method	245±10 °C
Melting temp.	ISO 294	235±10 °C
Vicat softening temp. B	ISO 306 B50	76°C
Vicat softening temp. A	ISO 306 A10	97°C

Additional info:

Recommended temperature for heated bed is ≥100°C. ABS-X is printed at high temperatures to make the final product extra strong. ABS-X can be used on all common desktop FDM or FFF technology 3D printers.

Storage: Cool and dry (15-25°C). This enhances the shelf life significantly.